

a label which is treated with a water activatable animal glue.

16. (original): A composition for forming an activatable hydrophillic layer on a surface of label stock, said composition comprising:

animal glue 30-95 wt %;
synthetic and/or natural polymer additive 5-65 wt %;
cross-linker 0-5 wt %;
humectant 0-15 wt %;
wetting agent 0-1 wt %;
defoamer 0-1 wt %;
anti-block additives 0-2 wt %;
slip additives 0-2 wt; and
Water balance to 100 wt %.

17. (original): A composition for activating a dried activatable hydrophillic layer on a surface of label stock, said composition, said composition comprising

cross-linker 1-10 wt %;
wetting agent 0-1 wt %;
defoamer 0-1 wt %;
thickener 0-2 wt %;
natural polymer 0-15 wt %;
synthetic polymer 0-10 wt %;
and water balance to 100%.

REMARKS

In response to the restriction requirement, the applicant elects Group I , claim 1-13 with traverse because there is a technical relationship between the separately grouped claims.

Under the ADMINISTRATIVE INSTRUCTIONS UNDER THE PCT, page AI-58, which is available as Annex B to APPENDIX T of the MPEP, if there is a technical relation between the

separately grouped claims, restriction should not be required. In this case, the separately grouped claims all use the same adhesive and this is a sufficient technical basis on which to link the claims. For these reasons, it is requested that the restriction requirement be withdrawn and an action be given on all claims.

Respectfully submitted,



James V. Costigan
Registration No. 25,669

Hedman & Costigan, P.C.
1185 Avenue of the Americas
New York, NY 10036
(212) 302-8989